

RECYCLING CONCRETE - AN OVERVIEW OF DEVELOPMENT AND CHALLENGES

Erik K. Lauritzen ⁽¹⁾

(1) DEMEX Consulting Engineers A/S, Denmark

Abstract ID Number: 193

Author contacts

Authors	E-Mail	Fax	Postal address
<u>Erik K. Lauritzen</u>	el@demex.dk	+45 48104300	DEMEX A/S, NIRAS, Sortemosevej 2, 3450 Allerød, Denmark

Contact person for the paper: Erik K. Lauritzen

Presenter of the paper during the Conference: Erik K. Lauritzen

Total number of pages of the paper (this one excluded): 9

RECYCLING OF CONCRETE – AN OVERVIEW OF DEVELOPMENT AND CHALLENGES

Erik K. Lauritzen⁽¹⁾

(1) DEMEX Consulting Engineers A/S, Denmark

Keywords: Recycling, reuse, concrete, demolition, post-war reconstruction

Abstract

This paper consists of an overview over the development of recycling of concrete and the use of concrete with recycled materials. The overview and strategic management of demolition waste is often missing when handling concrete demolition waste. The demolition, processing and recycling of the materials are often analysed separately. "High quality" recycling of concrete waste does not always correspond to production/use of the product with the highest value, but rather the most feasible product in a specific project or region. It is by analysing the whole disposal/ supply-chain including the substituted material, that best effects of recycling can be achieved. Demolition is most often the first, and not the last phase of a building's life. There is almost always a building where a new one is to be built.

Environmental issues are a growing concern in the world. There are a number of ways to include environmental issues when planning demolition and recycling activities. Overviews of methods for environmental evaluations as well as economical considerations are presented in the paper. The market for recycled materials in the world is commented, and integrated demolition and waste management in Kosovo and an analysis of the potential market in Hong Kong are presented as examples. Current challenges in the industry are how to control and handle polluted material. These issues will be discussed from a practical point of view. Moreover some aspects to consider with respect to future demolition when producing new concrete products are presented.

1. INTRODUCTION

Since Agenda 21, the Rio Declaration on Environment and Development, was launched in 1992 sustainable development has been one of the key issues of modern society. The recycling of Construction and Demolition waste (C&D waste) has emerged as a socio-economic priority within the European Union and a considerable amount of research and development has taken place in the frame of RILEM (*The international union of testing and research laboratories for materials and structures*). In 1981 European and Japanese members of RILEM took the initiative to complete the first RILEM technical committee on the demolition and recycling of concrete, including several material research projects in this field. The research of the RILEM technical committees on recycling has been published in proceedings from three international symposia held by RILEM in Antwerp, Belgium 1985 [1], in Tokyo, Japan, 1988 [2] and in Odense, Denmark, 1993 [3]. In 2000 the state-of-the-art-report of RILEM Technical Committee 165-SRM on Sustainable Raw Materials was edited by C.F. Hendriks and H.S. Pietersen [4].

Parallel to the work of RILEM, the recycling of concrete has taken place in USA. For example, the Federal Highway Association has implemented recycling of concrete pavements in reconstruction of high ways. American Concrete Institute (ACI) has also worked on recycling of concrete. Some years ago, ACI realized that even if concrete is an environmentally friendly material, Portland cement is the critical component of modern-day concrete. To address this issue and the relationship between sustainable development and concrete technology, the ACI Board of Direction, in 2000, formed a Task Group on Sustainable development and concrete technology. Its mission was to encourage the development and application of environmentally friendly, sustainable concrete materials, design and construction. One of the most important issues of sustainability was the use of recycled aggregate [5].

Fortunately, some ACI members had been far-sighted enough in 1985 to organize Committee 555 – Concrete with Recycled Materials. In 2001 the committee submitted a report “*Removal and Reuse of Hardened Concrete*” [6], which has established a very good basis for the future work of ACI on the sustainability and recycling of concrete. On the ACI Spring Conference 2003 the ACI Committee 555 arranged a seminar on recycling of building materials. The presented papers are published in a special ACI publication “*Recycling Concrete and Other Materials for Sustainable development, ACI Committee 555*” [7].

2. THE NEED FOR C&D WASTE MINIMIZATION

In all communities it has always been common practice to retrieve valuable materials from the arising waste, e.g. metals and building materials. After some decades in this century with an extensive "use-and-throw-away" philosophy it has been recognized that we cannot continue this uninhibited use of natural resources and pollution of the world with waste. It is necessary to change our habits and to revise former common practices within the building & construction industry, as well as within other industries, households, etc.

In many countries, industrial as well as developing, C&D waste is considered as harmless, inert waste, which does not give rise to problems. However, C&D waste consists of huge amounts of materials that are often deposited without any consideration, causing many problems and encouraging the illegal dumping of other kinds of waste. Whether C&D waste originates from clearing operations after natural disasters or from human-controlled activities, the utilization of such waste by recycling can provide opportunities for saving energy, time, resources and money [8, 9, 10]. Furthermore, recycling and the controlled management of C&D waste will mean that less land is used and better opportunities will be created for the handling of other kinds of waste.

3. C&D WASTE STREAMS IN THE EU AND USA

A large proportion of C&D waste derives from demolition, rehabilitation, and new construction following normal development, as well as from natural and technological disasters. For example, the production of building materials and goods involves surplus ready-mixed concrete, concrete elements, articles of wood etc., which can be classified as industrial waste.

In the European Union, whose population in 2000 was approximately 370 million, it is estimated that the annual generation of C&D waste is approximately 200- 300 million tons - equivalent to 0,5 - 1 ton per capita per year in very rough figures [8, 11].

Clear figures regarding recycling do not exist in every EU member country. An EU study calculated that an average of 28 % of all C&D waste was recycled in the late 1990s [12]. In the Netherlands 95 % of all C&D waste is recycled and in Denmark 90 % is recycled.

Most EU member countries have established goals for recycling that range from 50 % to 90 % of their C&D waste production, in order to substitute natural resources such as timber, steel and quarry materials. Recycled materials are generally less expensive than natural materials, and recycling in Germany, Holland and Denmark is less costly than disposal [8, 11, 12].

The C&D waste streams in the USA were assessed by Robert H. Brickner in 2002 [13]. It is estimated that the amount of C&D waste is 250 – 300 million tons per year (2002 figures) and that 20 – 30 % is recovered for recycling (1996 figures).

According to Metha [14] the global concrete industry uses approximately 10 billion tonnes of sand and rock each year and more than 1 billion tonnes of C&D waste are generated every year.

4. CHALLENGES OF RECYCLING

According to the EU Waste Directive on Prevention and reduction of Waste the key issues are:

- Recycling, reuse & recovery (R3) of waste
- Management and planning of CDW handling
- Polluter pay principle

This presentation will focus on recycling. C&D waste has a high recycling potential because the majority of it consists of masonry, concrete, and steel. In Europe up to around 90 % of C&D waste consists of concrete and masonry. Buildings erected before the middle of the last century were mainly constructed with masonry, and buildings in the second half of the century were mainly constructed with concrete. The situation in the USA is probably the same.

Based on a global overview [14] it is estimated that the potential of recycling is approximately 50 %, which is equal to approximately 500 million tons, which is equal to 5 % of the global consumption of sand and rock.

At present, only very limited amounts of C&D waste are recycled as high-value materials, such as recycled aggregates in new concrete. The majority of such waste is disposed of or used as fill. Since the amounts of C&D waste are constantly increasing, there are many reasons for focusing on methods that promote an increase in the recycling of C&D waste (dumping fees in Europe and the USA are typically from US\$ 20-50 per ton). Present results in Europe show very favorable recycling possibilities in this field.

From a purely economic point of view the recycling of building waste is only attractive when the recycled product is competitive with natural resources in relation to cost and quality.

Recycled materials will normally be competitive where there is a shortage of both raw materials and suitable deposit sites.

With the use of recycled materials, economic savings in the transportation of building waste and raw materials can be achieved. In larger recycling projects, such as urban development, renovation of motorways, or clearing of war/disaster-related damages, the total project cost will be dominated by transportation costs. These transportation costs involve the removal of demolition products and the supply of new building materials. In these cases the use of recycled materials is very attractive.

The prospects of systematic recycling of C&D rubble in various parts of the world have been analysed [8, 15]. In order of importance, the three main factors affecting the prospects of recycling C&D waste are

- population size and density,
- occurrence of and access to natural raw materials, and
- level of industrialisation.

5. OPPORTUNITIES FOR RECYCLING

In order to meet the challenges of recycling, it is necessary that all opportunities, barriers and obstacles are detected and considered. The opportunities must be exploited, which can for example involve the recycling of concrete and masonry into aggregate, substituting natural materials:

- Aggregate bound in concrete
- Unbound sub-base and base materials

The opportunities for the production of concrete from recycled concrete are generally described in the ACI 555 report [6]. The recycling of concrete waste in a global perspective is described by Torben C. Hansen and Erik K. Lauritzen [8], Mats Topping [16] and Mats Topping and Erik K. Lauritzen [17].

The overcoming of these barriers and obstacles must be planned and carried out through a long-term action plan combined with adequate research and development. Implementation of the necessary legal, economic and technical instruments requires that initiatives involving legislation and regulations be taken.

5.1 Economy

With a condition of market economy, the choice between recycled and natural materials depends on price and quality. The quality of concrete with recycled aggregates can be the same as that of concrete with natural aggregates, but recycled concrete aggregates are regarded with suspicion. Hence, recycled concrete materials will only be preferred where the price of such aggregates is considerably lower than that of the natural materials, even when the recycled aggregates meet given specifications.

Introducing economic instruments, which encourage recycling and the use of recycled materials, can overcome the economic barriers. As an example it should be mentioned that several countries have introduced special taxes and fees in favour of recycling. For example, in 1986 the Danish government introduced a tax on waste that is not recycled but disposed off at landfill sites. Today the tax is DKK 375 (approx. EURO 50) per ton of waste disposed off at landfill sites.

The major issues of the cost-benefit to society are:

- willingness to pay for the impact on the environment
- willingness to accept the impact on the environment

5.2 Policies & Strategies

C&D waste must be considered as a specific individual type of waste associated with the building and construction industry. It is important that the management and handling of waste is carried out by the industry itself. Generally, the building and construction industry is relatively conservative, and changes in normal procedures often take time and need long-term policies and strategies.

One of the most important barriers is the many different interests in building waste. Usually it is the environmental politicians, departments and public offices who prepare the policies and issues concerning waste recycling and reduction, whereas the building and construction industry is controlled by laws, departments and offices concerned with housing, construction and public works. To co-ordinate the interests of all parties, particularly with respect to the implementation of cleaner technologies in industry, it is necessary that long-term policies and strategies should first have been prepared and implemented.

Danish experience in this field has led to the recommendation that long-term strategies, e.g. for 10 years with respect to achieving goals for the recycling of C&D waste, should be adopted. These must then be continuously revised in accordance with the political situation, and followed up by adequate legislation and regulation at all levels - national, regional and local.

5.3 Certification of recycled materials

Demolition and crushing techniques for the production of recycled materials are well known and based on existing technologies. However, some changes in the demolition process, compared with traditional demolition, are required as described below. Even when recycled materials fulfil current standards for natural materials, and even when the prices can compete with the prices of natural materials, certain barriers still exist.

Owing to tradition and psychological barriers the general attitude towards recycling in the building and construction industry is largely prohibitive towards the utilization of recycled materials. Therefore, it is of great importance that recycled materials are officially certified and accepted by all parties in the building and construction industry. For example, in June 1994 RILEM published recommendations for concrete with recycled aggregate [18]. A review of international classification and certification of use of recycled C&D waste is presented by Henrichsen [11].

It is recommended that considerable emphasis be placed on specifying the areas of utilization and quality standards for recycled materials. These must be in accordance with the local demand in order to improve confidence in the recycled materials and solve problems regarding the responsibility of using such materials.

5.4 Planning demolition projects

A necessary condition for the recycling of building waste is careful sorting of the waste. Waste from new constructions and rehabilitation is sorted either at the production site or at a special treatment site. This separation into materials categories is fairly simple.

The sorting of waste from demolition is, however, a more complicated process. Demolition has until recently been regarded as a low technological process. Rapid demolition and disposal of structures were the main aims of the contractor. Special measures to separate the different types of materials were not possible, owing to the time factor, nor were they desired.

Optimal handling and recycling of C&D waste depends on the materials being sorted in-situ and in co-ordination with the demolition process using demolition technologies and methods as described in the ACI 555 report [6]. It is therefore necessary to alter the traditional methods of demolition and introduce selective demolition. This requires that before and during the demolition process an effective sorting of the different materials categories is carried out, thereby preventing any mix of materials leading to pollution of, for instance,

recyclable concrete/masonry rubble by wood, paper, cardboard, plastics etc. Since selective demolition takes more time than traditional demolition, detailed planning is considered as mandatory.

It is recommended that demolition projects should be planned and controlled in detail, in the same way as all other building and construction projects, to ensure selective demolition and correct handling of the demolition waste.

5.5 Education and information

The most important means to identify and exploit the opportunities and overcome the barriers and obstacles is education and information. It is necessary that the message and understanding of recycling be discussed at technical universities, among private enterprises and public servants.

6. INTEGRATED RESOURCE MANAGEMENT

In order to achieve the maximum benefit of recycling a management system must be established on a project basis in relation to a specific construction project, e.g. urban development master plan, or on a permanent basis in relation to long-term municipal and C&D waste management system.

The Integrated Resource Management System comprising environmentally and economically balanced management of the following elements:

- Demolition (selective demolition)
- Recycling, reuse recovery
- Handling of hazardous C&D waste materials and non-recyclable materials
- Transportation
- Substituting (saving) natural resources

A presumption of the success of the Integrated Resource Management System is that an effective co-operation between all stakeholders/decision makers has been established in order to avoid conflict of interests. Conflicts between recycling companies and raw materials companies, for example, could prevent all initiatives towards recycling in general.

The Integrated Resource Management can be implemented according to normal routines of project management in the construction industry, e.g.:

- Final Report. Descriptive document about the development and findings of the specific work packages and the project in general.
- National policies (legal and fiscal instruments)
- Regional strategies (control of C&D streams, stationary or mobile recycling plants)
- Concepts (high versus low value recycling)
- Feasibility studies (specific proposals for recycling)
- Computer optimisation (e.g. waste-resource streams and economic models)
- Master planning
- Design
- Supervision
- Quality & environmental management

The opportunities for recycling and integrated resource management depend on the size and the time frame of the project. In bigger projects, such as

- development of old industry sites, hospitals, airports, etc.
- reconstruction after disasters and wars
- urban renewal and development of cities

recycling of concrete and other building materials must be considered careful. Two examples and an on-going study are presented:

(1) Kosovo

In June 1999, the hostilities in Kosovo officially ceased and the huge task of reconstructing the province commenced. One of the major challenges faced from day one included cleaning the urban and rural areas of damaged buildings and rubble. It was initially estimated that nearly 10 million tonnes of demolition waste should be collected and handled.

Based on previous experiences with the recycling of rubble from the demolition of damaged buildings on the former confrontation line in Mostar (Bosnia & Herzegovina from 1995 to 1997), the Danish Ministry of Foreign Affairs (DANIDA) decided to establish a Building waste Management System, comprising demolition of damaged buildings and recycling of building waste materials in Kosovo. A robust mobile crusher and screening unit that could travel with the demolition teams and process the rubble at recycling depots were needed for this purpose.

During the project in Kosovo, all of the recycled materials produced were sold to both public and private clients. This 100% sales level has only been possible through extensive workshops and seminars demonstrating the use of the recycled gravel for road construction and as engineering fill. The main customers included NATO's forces in Kosovo, which required significant quantities of gravel for their army bases. Also local contractors have bought the recycled material for construction of roads.

Testing the recycled material was not possible in Kosovo since the laboratories had been damaged during the hostilities. So the Waste Demolition and Recycling organisation (WDR) managed by DEMEX in Kosovo had to "export" the gravel for materials testing in neighbouring Macedonia and then translate the results into Albanian for local use. This troublesome procedure did prove worthwhile in the end as the recycled materials complied with all the required Yugoslav materials specifications for road construction.

Also the ownership over the rubble had to be discussed. When it was recognised that WDR was able to turn the rubble into a valuable product, some of the building owners were concerned of "giving" their rubble away and on numerous occasions WDR had to barter with the village leaders.

This project has again proved that the recycling of the demolition waste generated from reconstruction activities after disasters and wars is a sustainable solution and an important contribution to waste management during this often difficult and chaotic phase.

(2) Kai Tak Recycling Facility

In 2001 DEMEX made a design of a recycling facility to be installed at the old abandoned Kai Tak airport in Hong Kong until the land was ready for development. The total generation of C&D waste materials forecast for the whole Hong Kong region for the year 2002 was approximately 13.7 million tonnes per year. This represented a daily generation rate of approximately 14,000 tons. It was estimated that 30% of the total C&D could be delivered to the recycling plant. The average total of 4,200 t/day has been used for the preliminary detailed design of the Kai Tak recycling facility.

A pilot C&D recycling facility comprised two crushers and two screening units setup in a single process line. Further expansion of the plant capacity would be required to go beyond 3,500 t/day.

The results of the feasibility study indicated a profitable business opportunity for recycling C&D materials in Hong Kong, with the condition that the land rent was set a zero HK\$. Entering the construction aggregates market at 80% of virgin materials prices, it was expected that the Kai Tak C&D facility would turn a health profit.

However, the major problem was that the political situation in Hong Kong in 2001 was not mature for the implementation of the C&D recycling project. In Europe, all inhabitants are

used to pay for waste collection and treatment of waste. It is evident that the driving forces of recycling are linked to economical instruments, of which waste fees and transportation cost are the most important issues.

In Hong Kong there has been a political tradition for free waste collection without any cost to the citizens. Therefore, there are no incitements for the construction sector to deliver their waste to the recycling plant, and the overall economy of the recycling will not be satisfactory.

This example shows clearly, that even though the need for recycling is clearly demonstrated, the political decision and the implementation of the *polluter pays principle* is a fundamental condition for recycling.

(3) The IRMA Project

In August 2003 a major European project on integrated resource management was launched with the objective of developing and demonstrating models and management tools for rehabilitation of buildings and recycling of building waste materials in urban renewal. The project is performed by 17 participants from 8 EU countries with support from the European Commission. The project is presented by García [19] at this conference.

7. GLOBAL VISIONS

The construction industry must aim at durability and sustainability as described by Metha [14]. A holistic life cycle based approach is recommended in order to reduce the environmental impact. Further it is mentioned that the resource efficiency of the concrete industry will increase by a factor of five if the service life of most structures built today were 250 years instead of the conventional 50.

Looking at recycling, it is estimated - based on a global C&D waste production of 1 billion tonnes per year - that potentially 50 % should be recycled and could substitute approximately 5 % of the global consumption of sand and rocks.

However, the truth is that there is a long way to go before this level of recycling can be attained in developing countries, where many other environmental problems must be prioritised. But there is no excuse for the industrialised nations not to start the implementation of Integrated Resource Management Systems, aiming of 90 % recycling and maximum substitution of natural resources. There is no doubt that results and experience from European research and development can be transferred to other parts of the world and enable natural (primary) raw materials to be replaced by recycled materials, especially in urban renewal and rehabilitation projects.

8. CONCLUSION

The development of technologies for the recycling of concrete and the market for various types of recycled concrete materials has proved the viability and sustainability of recycling concrete. The challenges of recycling are dominated by a very high potential of concrete waste all over the world and a demand for recycled materials in order to substitute natural resources. The opportunities for recycling are based on economics, policies & strategies, certification of recycled materials, planning of demolition projects, and education and information.

The success of recycling concrete today in some European countries is based on integrated resource management. The success of recycling in the future is based on global visions for the implementation of recycling concrete world-wide in order to save natural resources and protect the environment.

REFERENCES

- [1] Hansen Torben C., 1985, Proceedings of the EDA - RILEM International Symposium on Re-use of Concrete and Brick Materials, June 1985.
- [2] Kasai, Yoshio, 1988, Proceedings of the Second International RILEM Symposium on Demolition and Reuse of Concrete and Masonry, Chapman and Hall, Tokyo, 7-11 November 1988.
- [3] Lauritzen, Erik K., 1993, Proceedings of Third International RILEM Symposium on Demolition and Reuse of Concrete and Masonry, Guidelines for Demolition and Reuse of Concrete and Masonry, E. & F.N. Spon, Odense, Denmark, 24-27 October 1993.
- [4] Hendriks, C.F and Pietersen, H.S. (eds), 2000, "Sustainable Raw Materials – Construction and Demolition Waste (165-SRM)," State-of-the-Art Report of RILEM Technical Committee.
- [5] Malhotra, V.M., 2002, "Introduction: Sustainable Development and Concrete Technology," Concrete International, V. 24, No. 7, July 2002.
- [6] ACI Committee 555, 2001, "Removal and Reuse of Hardened Concrete (ACI 555R-01)," American Concrete Institute, Farmington Hills, MI.
- [7] Tony Lieu and Christian Meyer, Recycling Concrete and Other Materials for Sustainable development, ACI Committee 555 report SP-219, 2004, ACI, P.O. Box 9094, Farmington Hills, MI, USA
- [8] Lauritzen, Erik K. and Hansen, Torben C., 1997, "Demolition and Recycling 1986 – 1995," Danish Environmental Protection Agency, News.
- [9] Lauritzen, Erik K., 1994, "Economic and Environmental Benefits of Recycling Waste from the Construction and Demolition of Buildings," UNEP Industry and Environment, April-June 1994.
- [10] De Pauw, C. and Lauritzen, Erik K., 1994, "Disaster Planning, Structural Assessment, Demolition and Recycling," RILEM Report No. 9, E. & F.N. Spon, 1994.
- [11] Henrichsen, Anders, 2000, "Use of Recycled Aggregates in Europe," presented at Tokyo University, Japan, November 2000.
- [12] Symonds, Argus COWI and PRC Bouwcentrum, 2000, "Construction and Demolition Waste Management Practice and their Impact," February 2000, DG XI EU Commission.
- [13] Brickner, Robert H., 2002, "Recycling of Construction and Demolition Waste, Status and Issues in the USA," September-October 2002.
- [14] Metha, P. Kumar, 2002, "Greening of the Concrete Industry for Sustainable Development," Concrete International, July 2002.
- [15] Hansen, Torben C. and Lauritzen, Erik K., "Concrete Waste in a Global Perspective," presented at the ACI Spring Convention, Committee 555 April 1st 2003.
- [16] Topping, Mats, 2001, Management of Concrete Demolition Waste, Ph.D. thesis, Norwegian University of Science and Technology.
- [17] Topping, Mats and Lauritzen, Erik K., 2002, "Challenges of Concrete Constructions," University of Dundee, 5 – 11 September 2002.
- [18] RILEM Technical Committee TC-121, 1994, "Recommendation for Concrete with Recycled Aggregates," June 1994.
- [19] Inés García Sánchez and Erik K. Lauritzen, Integrated Decontamination and Rehabilitation of Buildings, Structures and Materials in Urban Renewal – A European Project for Sustainable City Concept, Fourth International RILEM Conference on the Use of recycled Materials in Buildings and Structures, Barcelona 9 – 11 November 2004